

Technical Data Sheet

Euro Colour 2K Thinner E 585, 2K Thinner E 500, 2K Thinner E500s, Epoxy Thinner AE 8320

Description: Solvent mixture developed for adjusting the viscosity of EURO COLOUR products, retardant, dissolve prior to use. They are formulated differently for optimize application in all working conditions.

Euro Colour 2K Thinner E 585, E 500, E 500s : 2K Thinner for 2K Paint system
Euro Colour epoxy Thinner AE 8320 : Thinner for Euro Colour Epoxy Primer

Work Instruction

Euro Colour 2K Thinner	Mixing Ratio (% by volume)*								Temperature Range (° C)		
	E 240, E242	E 321	E 333	AE 1860	Master Colour				20-25	25-35	35-45
					Standard Basecoat	Direct-Gloss 3:1	Direct-Gloss 4:1	1K Basecoat			
E 585	20	xx	xx	x	xx	xx	15-25	15-25	//	/	xx
E 500	20	20	2-5	x	20-25	15-20	15-25	15-25	//	//	xx
E 500s	20	20	Xx	x	20-25	15-20	15-25	xx	xx	/	//
AE 8320	x	x	x	25	x	x	x	x	/	/	/

* Mixing Ratio as after mixing with hardener or supplied.
** x = restricted xx not recommended / suitable // optimal



Products	Packages (lit)	Storability at 20° C (month)
Euro Colour 2K Thinner E 585	3.785-13.00	24
Euro Colour 2K Thinner E 500	1-3.785-13.00	24
Euro Colour 2K Thinner E 500s	3.785-13.00	24
Euro Colour Epoxy Thinner AE 8320	3.785	24

Safety Information

- Consult the chemical safety data sheet prior to use.
- Read the precautionary notice displayed on the container.
- Suggested protection suit and accessories must be used while working
- MSDS is available at distributors or the manufacture

VOC Regulated Areas

These directions refer to the use of products which may be restricted or require special mixing instructions in VOC regulated areas. Follow mixing and usage recommendations in the VOC Compliant Products Chart for your area.

Disclaimer: To the best of our knowledge, the information contained herein is accurate. However, neither the above named supplier nor any of its subsidiaries assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of suitability of any material is the sole responsibility of the user.

